


1900 Albany Place SE
P.O. Box 286
Orange City, IA 51041

800-747-3436 Fax 712-737-3893
www.oldmastrs.com

PRODUCT INFORMATION

H₂O® PICKLING CLEAR **ACRYLIC POLYURETHANE SEMI-GLOSS**

PRODUCT NO.	54201, 54204
GENERIC TYPE	Waterborne Acrylic Urethane Varnish
COLOR	Clear
GLOSS	50 to 65 @ 60°
SOLIDS BY WEIGHT	32.0%
SOLIDS BY VOLUME	29.0%
V.O.C.	450 grams/liter
THEORETICAL COVERAGE @ 1 MIL DFT	464 sq. ft. per gal.
COVERAGE @ RECOMMENDED DFT	250 to 500 sq. ft. per gal.
RECOMMENDED DFT PER COAT	1 to 2 Mils
WEIGHT PER GALLON	8.6 lbs.
FLASH POINT	Not applicable
USE	Step 2 in the Pickling System, used to topcoat H ₂ O® Pickling White Stain on interior wood surfaces. When used as a system, finish will not yellow.
VISCOSITY AT 77°F	30 to 40 sec. #4 Ford Cup
AVERAGE DRY TIME AT 70°F & 50% R.H.	Dry to touch in 15 minutes. Recoat after 1 to 2 hours.
RECOMMENDED THINNER	Water
APPLICATION	Nylon bristle brush, pad, roller, or spray. Thin with water up to 1 pint per gallon for spray applications.
SURFACE PREPARATION	The surface must be clean, dry, and free of wax, oil, grease, and products containing stearates. Remove all dust. Do not use a tack rag.
CLEAN UP	Soap and water.



PRODUCT INFORMATION

H₂O® PICKLING CLEAR ACRYLIC POLYURETHANE SEMI-GLOSS

DESCRIPTION: Old Masters® H₂O® Pickling Clear Acrylic Polyurethane is the second step in our two part Pickling System. This crystal clear, water reducible, interior topcoat seals, protects, and enhances the beauty of pickled and white wash stained wood. A fully compatible partner for our Pickling System Part 1 H₂O® Pickling White Stain results in a beautiful, durable finish that will not yellow over time. Its super hard finish is tough enough for wood floors, cabinets, doors, furniture, and table tops. H₂O® Pickling Clear dries quickly with low odor and cleans up easily with water. Non-flammable, non-toxic, safe formula.

THINNING: Thinning is not recommended, but, if necessary, a small amount of water may be added. For spray applications, up to one pint of water per gallon may be added.

SURFACE PREPARATION: The wood surface must be clean, dry, and free from dirt, wax or grease. If your project is to be stained white, we recommend Old Masters® H₂O® Pickling White Stain. Do not use over shellac, lacquer, filler, stains, or sealers containing stearates. Remove dust particles with a cloth dampened with water. Do not use a tack rag to remove dust since it may leave a residue that will interfere with adhesion.

APPLICATION: DO NOT SHAKE. Stir well before and during use to ensure evenness of the finish. Test the finish on an inconspicuous part of the surface prior to finishing. Apply with a nylon bristle brush, pad, short nap roller or spray. Airless tip sizes of .011 to .013 are recommended when spraying. Apply in full, even coats; if brushing, apply liberally and keep a wet edge, working quickly to ensure an even coat. Apply with care to prevent air bubbles in the finish. Large, flat surfaces may be rolled but must be quickly leveled off with a brush to prevent air entrapment. H₂O® Pickling Clear dries clear, even though it appears milky in the can.

Allow 2 to 4 hours before recoating. Do not recoat too soon. Be sure previous coat is thoroughly dry before recoating. Recoating too soon or when drying conditions are not ideal can produce a milky finish caused by moisture entrapment. Sand lightly between coats with very fine sandpaper to produce a finer finish. DO NOT USE STEEL WOOL. Remove sanding dust with a damp cloth. Three coats are recommended for greatest durability.

Note: Keep in mind that the white stain will be lightened and slightly subdued when the Pickling Clear is applied. The sheen of the clear coat softens the stain on the surface, yet enhances the depth and overall finish, much like looking through glass. H₂O® Pickling Clear is formulated not to yellow over time when applied over Old Masters® H₂O® Pickling White Stain. If your white stain is not Old Masters® Pickling Stain, the formulas may not be compatible. Always test your stain and topcoat before beginning a project to ensure you receive the results you expect.

SPREADING RATE: Coverage is approximately 300 to 400 square feet per gallon.

DRYING TIME: At 50% relative humidity and 70°F, H₂O® Pickling Clear will dry to touch within 30 minutes and be ready to recoat in 2 to 4 hours. Wait 24 hours before subjecting surfaces to light use. Care should be used during the first week after application as the finish is still curing to its ultimate hardness.

Note: **Never** allow long term exposure to excessive levels of moisture and/or cold temperatures. This can cause blushing and will result in a white milky finish.

CLEAN UP: Wash brushes and equipment in warm soapy water and rinse with water.

MAX. VOC: 350 grams/liter (2.92 lbs./gal.)

CAUTION!

Do not take internally. Close container after each use. Protect from freezing.
KEEP OUT OF REACH OF CHILDREN.

Limited Warranty

Since Old Masters® does not control the application of its products, nor the condition of the surfaces to which they are applied, a Limited Warranty is provided. If the products do not perform as specified, for whatever reason, Old Masters® liability will under no circumstances exceed replacement of the product.

OLD MASTERS®
1900 ALBANY PLACE SE
ORANGE CITY, IA 51041